QUARZI 3D - Technical specifications

ISO 13006 - EN 14411 - ISO 10545 Standards

Nominal sizes (cm): **15x61**	Thickness (mm) : **7-11**
Sides: **Natural**	Surface: **3D**
	Product Group: **BIa-GL**

Technical characteristics		**Test method**	**EN 14411 and ISO 13006 requirements**	**Italcer Average values**
Dimensions	Length and width	ISO 10545-2	±0.6% and ± 2.0mm Rect. : ±0.3% and ± 1.0mm	Compliant
	Straightness of sides	ISO 10545-2	±0.5% and ± 1.5mm Rect. : ±0.3% and ± 0.8mm	Compliant
	Rectangularity	ISO 10545-2	±0.5% and ± 2.0mm Rect. : ±0.3% and ± 1.5mm	Compliant
	Flatness	ISO 10545-2	±0.5% and ± 2.0mm Rect. : ±0.4% and ± 1.8mm	Compliant
	Thickness	ISO 10545-2	±5% and ± 0.5mm	Compliant
Water absorption		ISO 10545-3	≤ 0.5%	Compliant
Modulus of rupture		ISO 10545-4	≥ 35 N/mm^2	Compliant
Breaking strength (S)		ISO 10545-4	≥ 1300 N	Compliant
Linear thermal expansion		ISO 10545-8	Declared value	$\alpha \leq 7.1x10^{-6}\ °C^{-1}$
Thermal shock resistance		ISO 10545-9	No alterations	Resistant
Frost resistance		ISO 10545-12	No alterations	Resistant
Chemical resistance		ISO 10545-13	Declared value	LA – HA
Household chemicals resistance		ISO 10545-13	B min.	A
Stain resistance		ISO 10545-14	Class 3 min.	5
Mohs Hardness		UNI EN 101	5 Min.	6
Shade variation		ANSI A 137.1	Not required	V4
Fire reaction		UNI EN 13501-1	-	$A1_{FL}$ class
Thermal Conductivity		EN 12524	Not required	λ = 1.3 W/m·°K
Light and colour fastness		DIN 51094	Not required	No variations

Rubiera, June 11 2026

Italcer Quality Department